CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER IS/ISO/IEC 17025:2017
4, 7TH MAIN MALLESHWARAM, BANGALORE -5

QC ABSTRACT

NAME OF WORK: Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kaveripuragere

SL NO	Item Of Work	Name of Test	Frequency of Testing/Quantity	Previous Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Fineness by Air permeability method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Brick	Compressive Strength	One Test		1	1
		WATER ABSORPTION	One Test		1	1
		EFFLORESCENCE	One Test		1	1
		DIMENSIONS AND TOLERANCES	One Test		1	1
6	Cement Concrete Pavement (M30)	Compressive Strength(7days and 28days)	3 set /15-30 cum	18.58	6	6
7	Mortar Sand	Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
		Compacted Bulk Density	One Test		1	1
		Loose Bulk Density	One Test		1	1
		SIEVE ANALYSIS	One Test		1	1

Assl. Executive Engineer
Project Division
Yelahanka Zone

M : 9972924526 | Tel : +91 80 23444801 | e : rechanot30@yahoo.co.in, civilpropert@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2022-12-27-25** **Date: 29-11-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone,
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer's Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-11-22
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 (RA 2021) DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, (RA 2018) Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, (RA 2019) Determination of Soundness, Clause 5, Clause 6 IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, (RA 2019) Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11, (RA 2019)DETERMINATION OF DENSITY , Clause 6
Date of test	:	27-11-22
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.2	_
2	Finess by Air permeablity method (m^2/kg,Min)	249.5	225m^2/kg, Min
3	Density (gm/cc)	3.11	_
4	Standard Consistency (%)	27.5%	Not specified
5	Initial Setting time	170 minutes	Not less than 30 minutes
6	Final Setting time	260 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2022-12-27-25** **Date: 26-12-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer's Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-11-22
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, (RA 2019) Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, (RA 2019) Determination of Compressive Strength, Clause 6
Date of test	:	27-11-22
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6650@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2022-12-27-25** **Date: 29-11-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer's Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	26-11-22
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2021 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	26-11-22

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	211	211	1.4	98.6	90-100
3	20 mm	7355	7566	50.4	49.6	30-70
4	10 mm	4219	11785	78.6	21.4	10-35
5	4.75 mm	2855	14640	97.6	2.4	0-5
6	Pan	360	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rpchan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2022-12-27-25** **Date: 29-11-22**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.6	
3	Specific Gravity	2.66	–
4	Bulk Density(Loose) (Kg/l)	1.54	–
5	Bulk Density(Compacted) (Kg/l)	1.58	–
6	Water Absorption(%)	0.22	–

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2022-12-27-25** **Date: 28-11-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-11-22
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2021 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	26-11-22

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	214	214	4.3	95.7	90-100
3	10 mm	2285	2499	50.0	50.0	25-55
4	4.75 mm	2378	4877	97.5	2.5	0-10
5	Pan	123	5000	100	0	–

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2022-12-27-25** **Date: 28-11-22**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.7	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	13.2	
3	Specific Gravity	2.56	–
4	Bulk Density(Loose) (Kg/l)	1.52	–
5	Bulk Density(Compacted) (Kg/l)	1.56	–
6	Water Absorption(%)	0.23	–
7	Aggregate crushing Value(%)	25.6	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP Bangalore-92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2022-12-27-25**

Date: 28-11-22

Customer : Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara

Agency : Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065

Customer's Reference : EE(Project)/Ynk.Zone/WO/93/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-11-22

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2021
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 26-11-22

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	32	32	3.2	96.8	90-100	90-100	90-100	95-100
3	2.36 mm	72	104	10.4	89.6	60-95	75-100	85-100	95-100
4	1.18 mm	248	352	35.2	64.8	30-70	55-90	75-100	90-100
5	600 micron	245	597	59.7	40.3	15-34	35-59	60-79	80-100
6	300 micron	215	812	81.2	18.8	5-20	8-30	12-40	15-50
7	150 micron	125	937	93.7	6.3	0-10	0-10	0-10	0-15
8	Pan	63	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2022-12-27-25**

Date: 28-11-22

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.45	–
2	Specific Gravity	2.57	–
3	Material finer than 75 micron(%)	6.1	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT OF PHYSICAL REQUIREMENTS OF BRICKS

Lab ID	:	**CP-2022-12-27-25** **Date: 12-12-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer's Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-12-22
Identification Mark on Brick	:	Wire Cut Brick
Reference to BIS codes	:	IS 1077 : 1992 (RA 2021) Common Burnt Clay Building Bricks-Specification IS 3495 (Part 1 to 3) : 1992(RA 2019) Method of Tests Burnt Clay Building Bricks Part 1:Determination of Compressive Strength, (Cl 4.2.3) Part 2:Determination of Water Absorption,(Cl 4.1.3) Part 3: Determination of Efflorescence, (Cl 4)
Date of test	:	05-12-22

COMPRESSIVE STRENGTH

Sl.No.	Length (mm)	Breadth (mm)	Area (mm^2)	Failure Load (KN)	Compressive strength of individual bricks (N/mm^2)	Acceptablity as per IS 1077:1992, Clause 7.1
1	232.96	107.56	25057	206.7	8.2	The bricks shall have a minimum average compressive strength for various classes as given in Table 1 of IS 1077: 1992. The compressive strength of any individual bricks shall not fall below the minimum compressive strength specified for the corresponding class of brick by more than 15%.
2	232.60	110.03	25593	197.6	7.7	
3	230.45	108.69	25048	201.3	8.0	
4	231.85	107.86	25007	199.5	8.0	
5	228.18	109.56	24999	194.6	7.8	
Average of 5 bricks					**8.0**	

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore-92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

Lab ID : **CP-2022-12-27-25** **Date: 12-12-22**

WATER ABSORPTION:

Sl.No.	Dry Weight	Wet Weight	Water Absorption(%)	Acceptablity as per IS 1077:1992, Clause 7.2
1	2.856	3.115	9.1	The water Absorption of bricks shall not be more than 20% by weight upto class 12.5 and 15% by weight for higher classes.
2	2.963	3.265	10.2	
3	2.857	3.125	9.4	
4	2.958	3.268	10.5	
5	2.963	3.285	10.9	
Average Water Absorption(%)			**10.0**	

EFFLORESCENCE:

Sl.No.	Length (mm)	Breadth (mm)	Area (mm^2)	Efflorescence	Acceptablity as per IS 1077:1992, Clause 7.3
1	228.16	108.98	24865	Slight	The efflorescence shall not be more than 'moderate" upto class 12.5 and "slight" for higher classes.
2	229.86	109.18	25096	Moderate	
3	229.32	108.39	24856	Moderate	
4	230.19	107.98	24856	Moderate	
5	228.13	109.19	24910	Moderate	

DIMENSIONS AND TOLERANCES

Sl.No.	Dimensions obtained for 20 bricks(mm)		Acceptability as per IS 1077:1992, Clause 6.2(b)
1	Length	4625	4520 to 4680 mm
2	Width	2190	2160 to 2240 mm
3	Height	1385	1360 to 1440 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2022-12-27-25

Date: 23/12/2022

Customer : Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara

Agency : Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065

Customer's Reference : EE(Project)/Ynk.Zone/WO/93/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-12-22

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/12/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen	Cross sectional area	Weight of the sample	Failure Load	Compressive strength	Average Compressive Strength
					(mm)	(Sq.mm)	(kg)	(KN)	(N/mm^2)	(N/mm^2)
1	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	149.54 X 151.16 X 150.18	22605	8.546	571.5	25.3	25.3
2	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	150.53 X 151.97 X 149.82	22875	8.604	599.8	26.2	
3	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	150.34 X 151.02 X 151.98	22705	8.621	553.7	24.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : CP-2022-12-27-25

Customer : Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.

Date: 23/12/2022

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara

Agency : Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065

Customer's Reference : EE(Project)/Ynk.Zone/WO/93/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-12-22

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/12/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	150.52 X 151.81 X 151.67	22851	8.858	588.4	25.7	25.6
2	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	149.14 X 151.80 X 149.71	22640	8.734	606.5	26.8	
3	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	151.04 X 151.19 X 151.81	22836	8.230	555.2	24.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2022-12-27-25

Date: 23/12/2022

Customer : Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara

Agency : Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065

Customer's Reference : EE(Project)/Ynk.Zone/WO/93/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-12-22

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 (RA 2018) Methods of Tests for Strength of Concrete Cl.5

Date of test : 23/12/2022

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	149.72 X 149.87 X 150.39	22439	8.401	571.3	25.5	
2	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	151.31 X 150.09 X 149.70	22709	8.457	611.0	26.9	25.6
3	Cement Concrete Pavement	M30	16/12/2022	23/12/2022	149.80 X 149.84 X 149.98	22445	8.774	549.0	24.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned by TapScanner

Format No: CP/TF/2017

TEST REPORT FOR SAND MASONRY MORTARS

Lab ID	:	**CP-2022-12-27-25** **Date: 08-12-22**
Customer	:	Assistant Executive Engineer, Project Sub Division, Yelahanka Zone, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Maintenance of UGD Lines in Singapura Areas in Ward No. 11 Kuvempunagara
Agency	:	Sri. S. Somashekar, #90, New No. 441/15, Allalasandra, GKVK Layout, Bangalore-560 065
Customer's Reference	:	EE(Project)/Ynk.Zone/WO/93/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-12-22
Sample Type	:	Fine Aggregate, M.Sand for Mortar
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2116-1980 (RA-2007) (Specification for Sand for Masonry Mortars) IS: 2386 :1963(Part - 1, 3) RA2021 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	05-12-22
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS: 2116-1980 (RA-2007)
1	4.75 mm	0	0	0	100	100
2	2.36 mm	75	75	7.5	92.5	90-100
3	1.18 mm	210	285	28.5	71.5	70-100
4	600 micron	138	423	42.3	57.7	40-100
5	300 micron	113	536	53.6	46.4	5-70
6	150 micron	328	864	86.4	13.6	0-15
7	Pan	136	1000	100.0	0.0	0

CIVIL Pro Sig..... Date..... BANGALORE

Asst. Executive Engineer, Project Division, Yelahanka Zone, BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY & ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT FOR SAND MASONRY MORTARS

Lab ID : **CP-2022-12-27-25** **Date: 08-12-22**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	3.16	–
2	Specific Gravity	2.53	–
3	Material finer than 75 micron(%)	13.6	Crushed Fine aggregate Max 15%
4	Compacted Bulk Density (Kg/litre)	1.92	–
5	Loose Bulk Density (Kg/litre)	1.75	–

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN

Authorized Signatory

Quality Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by TapScanner